# SPECIFICATIONS FOR NICHIA CHIP TYPE WHITE LED MODEL: NESW064T

NICHIA CORPORATION

#### **1.SPECIFICATIONS**

| (1) Absolute  | Maximum       | Ratings |
|---------------|---------------|---------|
| (1) 110001000 | 1/1u/1111ulli | ruungo  |

| 1) Absolute Maximum Ratings | -      |                          | (Ta=25°C)  |
|-----------------------------|--------|--------------------------|------------|
| Item                        | Symbol | Absolute Maximum Rating  | Unit       |
| Forward Current             | IF     | 30                       | mA         |
| Pulse Forward Current       | IFP    | 100                      | mA         |
| Allowable Reverse Current   | Ir     | 85                       | mA         |
| Power Dissipation           | Pd     | 105                      | mW         |
| Operating Temperature       | Topr   | -40 ~ +110               | °C         |
| Storage Temperature         | Tstg   | -40 ~ +110               | °C         |
| Dice Temperature            | Tj     | 125                      | °C         |
| Soldering Temperature       | Tsld   | Reflow Soldering : 260°C | for 10sec. |
|                             |        | Hand Soldering : 350°C   | for 3sec.  |

IFP Conditions : Pulse Width  $\leq 10$  msec. and Duty  $\leq 1/10$ 

#### (2) Thermal Characteristics

| 2) Thermal Characte | eristics |      | (Ta=25°C) |
|---------------------|----------|------|-----------|
| Item                | Symbol   | Тур. | Unit      |
| II                  | Rja      | 360  | °C/W      |
| Heat resistance     | Rjs      | 180  | °C/W      |

\* Rja = Heat resistance from Dice to Ambient temperature (Ta)

Rjs = Heat resistance from Dice to Solder temperature of Cathode Side (Ts)

\* Using Nichia standard circuit board FR4, t=1.6mm, Copper foil, t=35µm

#### (3) Initial Electrical/Optical Characteristics

| 3) Initial Electrical/Optical ( | (] | Га=25°С)  |           |        |      |      |
|---------------------------------|----|-----------|-----------|--------|------|------|
| Item Symbol Condition Typ.      |    |           |           |        | Max. | Unit |
| Forward Voltage                 | VF | IF=20[mA] | (3.1)     | 3.5    | V    |      |
| Luminous Intensity              |    | Iv        | IF=30[mA] | (1600) | -    | mcd  |
| Luminous Intensity              |    | Iv        | IF=20[mA] | (1200) | -    | mcd  |
| <pre></pre>                     | Х  | -         | IF=20[mA] | 0.31   | -    | -    |
| Chromaticity Coordinate         | у  | -         | IF=20[mA] | 0.32   | _    | -    |

\* Please refer to CIE 1931 chromaticity diagram.

| (4 | ) Ranking          |        |        |           |      | Γ)   | `a=25°C) |
|----|--------------------|--------|--------|-----------|------|------|----------|
|    | Item               |        | Symbol | Condition | Min. | Max. | Unit     |
|    |                    | Rank V | Iv     | IF=20[mA] | 1440 | 2000 | mcd      |
|    | Luminous Intensity | Rank U | Iv     | IF=20[mA] | 1000 | 1440 | mcd      |
|    |                    | Rank T | Iv     | IF=20[mA] | 720  | 1000 | mcd      |

\* Luminous Intensity Measurement allowance is  $\pm$  10%.

**Color Ranks** 

|   | Rank a0 |       |       |       |  |
|---|---------|-------|-------|-------|--|
| Х | 0.280   | 0.264 | 0.283 | 0.296 |  |
| у | 0.248   | 0.267 | 0.305 | 0.276 |  |

 $(IF=20mA,Ta=25^{\circ}C)$ 

|   |       | (1r-2011A, 1a-25C) |       |       |  |  |  |
|---|-------|--------------------|-------|-------|--|--|--|
|   |       | Rank b1            |       |       |  |  |  |
| Х | 0.287 | 0.283              | 0.330 | 0.330 |  |  |  |
| у | 0.295 | 0.305              | 0.360 | 0.339 |  |  |  |

|   |       | Rank b2 |       |       |  |  |
|---|-------|---------|-------|-------|--|--|
| Х | 0.296 | 0.287   | 0.330 | 0.330 |  |  |
| у | 0.276 | 0.295   | 0.339 | 0.318 |  |  |

|   | Rank c0 |       |       |       |  |  |
|---|---------|-------|-------|-------|--|--|
| Х | 0.330   | 0.330 | 0.361 | 0.356 |  |  |
| у | 0.318   | 0.360 | 0.385 | 0.351 |  |  |

\* Color Coordinates Measurement allowance is  $\pm 0.01$ .

\* One delivery will include up to two consecutive color ranks and three luminous intensity ranks of the products. The quantity-ratio of the ranks is decided by Nichia.

# 2. INITIAL OPTICAL/ELECTRICAL CHARACTERISTICS Please refer to figure's page.

# 3.OUTLINE DIMENSIONS AND MATERIALS

Please refer to figure's page.

|           |    | C 11      |   |
|-----------|----|-----------|---|
| Material  | 26 | tollowe   | • |
| wiaterial | as | 10110 w 5 | , |

| Package             | : | Heat-Resistant Polymer                    |
|---------------------|---|---|
| Encapsulating Resin | : | Silicone Resin (with Diffused + Phosphor) |
| Electrodes          | : | Ag Plating Copper Alloy                   |

#### 4.PACKAGING

 $\cdot$  The LEDs are packed in cardboard boxes after taping.

Please refer to figure's page.

The label on the minimum packing unit shows ; Part Number, Lot Number, Ranking, Quantity

- · In order to protect the LEDs from mechanical shock, we pack them in cardboard boxes for transportation.
- $\cdot$  The LEDs may be damaged if the boxes are dropped or receive a strong impact against them, so precautions must be taken to prevent any damage.
- $\cdot$  The boxes are not water resistant and therefore must be kept away from water and moisture.
- · When the LEDs are transported, we recommend that you use the same packing method as Nichia.

#### 5.LOT NUMBER

The first six digits number shows lot number.

The lot number is composed of the following characters;

 $\bigcirc \Box \times \times \times \times \cdot \bigtriangleup$ 

○ - Year (5 for 2005, 6 for 2006)

 $\Box$  - Month (1 for Jan., 9 for Sep., A for Oct., B for Nov.)

 $\times \times \times \times$  - Nichia's Product Number

- $\triangle$  Ranking by Color Coordinates
- Ranking by Luminous Intensity

# 6.RELIABILITY (1) TEST ITEMS AND RESULTS

|                             | Standard      |   |                   | Number of |
|-----------------------------|---------------|---|-------------------|-----------|
| Test Item                   | Test Method   | Test Conditions   | Note              | Damaged   |
| Resistance to               | JEITA ED-4701 | Tsld=260°C, 10sec.  | 2 times           | 0/22      |
| Soldering Heat              | 300 301       | (Pre treatment 30°C,70%,168hrs.)                                    |                   |           |
| (Reflow Soldering)          |               |   |                   |           |
| Solderability               | JEITA ED-4701 | Tsld= $215 \pm 5^{\circ}$ C, 3sec.                                  | 1 time            | 0/22      |
| (Reflow Soldering)          | 300 303       | (using flux, Lead Solder)   | over 95%          |           |
| Thermal Shock               | JEITA ED-4701 | -40°C ~ 110°C   | 100 cycles        | 0/100     |
|                             | 300 307       | 1min. (10sec.) 1min.  |                   |           |
|                             |               | (Pre treatment 30°C,70%,168hrs.)                                    |                   |           |
| Temperature Cycle           | JEITA ED-4701 | $-40^{\circ}$ C ~ $25^{\circ}$ C ~ $110^{\circ}$ C ~ $25^{\circ}$ C | 100 cycles        | 0/100     |
|                             | 100 105       | 30min. 5min. 30min. 5min.   |                   |           |
| Moisture Resistance Cyclic  | JEITA ED-4701 | $25^{\circ}C \sim 65^{\circ}C \sim -10^{\circ}C$                    | 10 cycles         | 0/100     |
|                             | 200 203       | 90%RH 24hrs./1cycle   |                   |           |
| High Temperature Storage    | JEITA ED-4701 | Ta=110°C  | 1000 hrs.         | 0/100     |
|                             | 200 201       |   |                   |           |
| Temperature Humidity        | JEITA ED-4701 | Ta=60°C, RH=90%   | 1000 hrs.         | 0/100     |
| Storage                     | 100 103       |   |                   |           |
| Low Temperature Storage     | JEITA ED-4701 | $Ta=-40^{\circ}C$   | 1000 hrs.         | 0/100     |
|                             | 200 202       |   |                   |           |
| Steady State Operating Life |               | Ta=25°C, IF=30mA  | 1000 hrs.         | 0/100     |
| **                          |               |   |                   |           |
| Steady State Operating Life |               | Ta=85°C, IF=25mA  | 1000 hrs.         | 0/100     |
| of High Temperature **      |               |   |                   |           |
| Steady State Operating Life |               | 60°C, RH=90%, IF=20mA   | 1000 hrs.         | 0/100     |
| of High Humidity Heat **    |               |   |                   |           |
| Steady State Operating Life |               | Ta=-40°C, IF=20mA   | 1000 hrs.         | 0/100     |
| of Low Temperature **       |               |   | 1000 110          | 0/100     |
| Permanence of Marking       | JEITA ED-4701 | Solvent : Isopropyl Alcohol   | 1 time            | 0/22      |
| g                           | 500 501       | Solvent Temperature : 20 ~ 25°C                                     | 1 11110           | 0/ ==     |
|                             | 000001        | Dipping Time : 5 min.   |                   |           |
| Vibration                   | JEITA ED-4701 | 200m/s <sup>2</sup> , 100 ~ 2000Hz (Sweep 4min.)                    | 4 times           | 0/10      |
|                             | 400 403       | 48min., 3directions   |                   | 5/10      |
| Drop                        |               | 75cm  | 3 times           | 0/10      |
| Electrostatic Discharge     | JEITA ED-4701 | R=1.5kΩ, C=100pF  | 3 times           | 0/22      |
|                             | 300 304       | Test Voltage=2kV  | Negative/Positive |           |

## (2) CRITERIA FOR JUDGING DAMAGE

|                                      |        |                 | Criteria for Judgement |               |
|--------------------------------------|--------|-----------------|------------------------|---------------|
| Item                                 | Symbol | Test Conditions | Min.                   | Max.          |
| Forward Voltage                      | VF     | IF=20mA         | -                      | U.S.L.*)× 1.1 |
| Luminous Intensity<br>Condition 1    | Iv     | IF=20mA         | L.S.L.**)× 0.7         | -             |
| Luminous Intensity<br>Condition 2 ** | Iv     | IF=20mA         | L.S.L.**)× 0.5         | -             |

\*) U.S.L. : Upper Standard Level \*\*) L.S.L. : Lower Standard Level \*\* These test items are jugged by the criteria of Luminous Intensity Condition 2.

# 7.CAUTIONS

The LEDs are devices which are materialized by combining Blue LEDs and special phosphors. Consequently, the color of the LEDs is changed a little by an operating current. Care should be taken after due consideration when using LEDs.

(1) Moisture Proof Package

• When moisture is absorbed into the SMT package it may vaporize and expand during soldering. There is a possibility that this can cause exfoliation of the contacts and damage to the optical characteristics of the LEDs. For this reason, the moisture proof package is used to keep moisture to a minimum in the package.

• The moisture proof package is made of an aluminum moisture proof bag. A package of a moisture absorbent material (silica gel) is inserted into the aluminum moisture proof bag. The silica gel changes its color from blue to pink as it absorbs moisture.

#### (2) Storage

- · Storage Conditions
  - Before opening the package :

The LEDs should be kept at 30°C or less and 90%RH or less. The LEDs should be used within a year. When storing the LEDs, moisture proof packaging with absorbent material (silica gel) is recommended.

After opening the package :

The LEDs should be kept at 30°C or less and 70%RH or less. The LEDs should be soldered within 168 hours (7days) after opening the package. If unused LEDs remain, they should be stored in moisture proof packages, such as sealed containers with packages of moisture absorbent material (silica gel). It is also recommended to return the LEDs to the original moisture proof bag again.

• If the moisture absorbent material (silica gel) has faded away or the LEDs have exceeded the storage time, baking treatment should be performed using the following conditions.

Baking treatment : more than 24 hours at  $65\pm5^\circ C$ 

- Nichia LED electrodes and leadframes are silver plated copper alloy. The silver surface may be affected by environments which contain corrosive substances. Please avoid conditions which may cause the LED to corrode, tarnish or discolor. This corrosion or discoloration might lower solderability or might affect on optical characteristics.
- Please avoid rapid transitions in ambient temperature, especially in high humidity environments where condensation can occur.

#### (3) Heat Generation

• Thermal design of the end product is of paramount importance. Please consider the heat generation of the LED when making the system design. The coefficient of temperature increase per input electric power is affected by the thermal resistance of the circuit board and density of LED placement on the board, as well as other components. It is necessary to avoid intense heat generation and operate within the maximum ratings given in this specification.

• The operating current should be decided after considering the ambient maximum temperature of LEDs.

(4) Soldering Conditions


The LEDs can be soldered in place using the reflow soldering method. Nichia cannot make a guarantee on the LEDs after they have been assembled using the dip soldering method.
Recommended soldering conditions

| Reflow Soldering |               |                  | Hand Soldering |                 |
|------------------|---------------|------------------|----------------|-----------------|
|                  | Lead Solder   | Lead-free Solder |                |                 |
| Pre-heat         | 120 ~ 150°C   | 180 ~ 200°C      | Temperature    | 350°C Max.      |
| Pre-heat time    | 120 sec. Max. | 120 sec. Max.    | Soldering time | 3 sec. Max.     |
| Peak             | 240°C Max.    | 260°C Max.       |                | (one time only) |
| temperature      |               |                  |                |                 |
| Soldering time   | 10 sec. Max.  | 10 sec. Max.     |                |                 |
| Condition        | refer to      | refer to         |                |                 |
|                  | Temperature   | Temperature      |                |                 |
|                  | - profile ①.  | - profile ②.     |                |                 |
|                  |               | $(N_2 reflow is$ |                |                 |
|                  |               | recommended.)    |                |                 |


\* Although the recommended soldering conditions are specified in the above table, reflow or hand soldering at the lowest possible temperature is desirable for the LEDs.

\* A rapid-rate process is not recommended for cooling the LEDs down from the peak temperature. [Temperature-profile (Surface of circuit board)]

Use the conditions shown to the under figure.



[Recommended soldering pad design] Use the following conditions shown in the figure.



Solder resist

(Unit : mm)

• Occasionally there is a brightness decrease caused by the influence of heat or ambient atmosphere during air reflow. It is recommended that the User use the nitrogen reflow method.

- The encapsulated material of the LEDs is silicone. Therefore the LEDs have a soft surface on the top of package. The pressure to the top surface will be influence to the reliability of the LEDs. Precautions should be taken to avoid the strong pressure on the encapsulated part. So when using the chip mounter, the picking up nozzle that does not affect the silicone resin should be used.
- Repairing should not be done after the LEDs have been soldered. When repairing is unavoidable, a double-head soldering iron should be used. It should be confirmed beforehand whether the characteristics of the LEDs will or will not be damaged by repairing.
- Reflow soldering should not be done more than two times.
- $\cdot$  When soldering, do not put stress on the LEDs during heating.
- · After soldering, do not warp the circuit board.


# (5) Cleaning

- It is recommended that isopropyl alcohol be used as a solvent for cleaning the LEDs. When using other solvents, it should be confirmed beforehand whether the solvents will dissolve the package and the resin or not. Freon solvents should not be used to clean the LEDs because of worldwide regulations.
- Do not clean the LEDs by the ultrasonic. When it is absolutely necessary, the influence of ultrasonic cleaning on the LEDs depends on factors such as ultrasonic power and the assembled condition. Before cleaning, a pre-test should be done to confirm whether any damage to the LEDs will occur.
- (6) Static Electricity
  - $\cdot$  Static electricity or surge voltage damages the LEDs.
  - It is recommended that a wrist band or an anti-electrostatic glove be used when handling the LEDs.
- All devices, equipment and machinery must be properly grounded. It is recommended that precautions be taken against surge voltage to the equipment that mounts the LEDs.
- When inspecting the final products in which LEDs were assembled, it is recommended to check whether the assembled LEDs are damaged by static electricity or not. It is easy to find static-damaged LEDs by a light-on test or a VF test at a lower current (below 1mA is recommended).
- Damaged LEDs will show some unusual characteristics such as the forward voltage becomes lower, or the LEDs do not light at the low current.


Criteria : (VF > 2.0V at IF=0.5mA)

# (7) Others

- $\cdot$  NESW064 complies with RoHS Directive.
- $\cdot$  The LED light output is strong enough to injure human eyes. Precautions must be taken to prevent looking directly at the LEDs with unaided eyes for more than a few seconds.
- Flashing lights have been known to cause discomfort in people; you can prevent this by taking precautions during use. Also, people should be cautious when using equipment that has had LEDs incorporated into it.
- The LEDs described in this brochure are intended to be used for ordinary electronic equipment (such as office equipment, communications equipment, measurement instruments and household appliances). Consult Nichia's sales staff in advance for information on the applications in which exceptional quality and reliability are required, particularly when the failure or malfunction of the LEDs may directly jeopardize life or health (such as for airplanes, aerospace, submersible repeaters, nuclear reactor control systems, automobiles, traffic control equipment, life support systems and safety devices).
- User shall not reverse engineer by disassembling or analysis of the LEDs without having prior written consent from Nichia. When defective LEDs are found, the User shall inform Nichia directly before disassembling or analysis.
- $\cdot$  The formal specifications must be exchanged and signed by both parties before large volume purchase begins.
- The appearance and specifications of the product may be modified for improvement without notice.





\* Color Coordinates Measurement allowance is  $\pm 0.01$ .




ķ

Nichia STSE-CC6049B <Cat.No.060831>





Nichia STSE-CC6049B <Cat.No.060831>



Nichia STSE-CC6049B <Cat.No.060831>

